9

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.	Gain. oz.	dec.	Description of Bullion.
Febry 24th	364	Harry Murray	29	06	28	98		08	28			Bars
	5	G. C. Thompson	21	23	18	94	2	29	10 90			Jewelry & Wtch Cases
	6	J. C. Heiston	17	78	17	63		15	83			Bar
	7	B. Levy	34	94	34	89		05	14			Bars
	8	G. C. Thompson	26	04	23	12	2	92	11 23			Jewelry & Silver
	9	Wm. H. Lee	56	40	56	39		01	02			Bar
	70	G. C. Thompson	11	24	8	01	3	23	29 27			Jewelry
	1	Do	31	10	18	79	2	31	11 00			Jewelry & Wtch Cases
	2	Do	9	48	5	06	4	42	49 11			Jewelry & Bars
	3	J. C. Meeks	26	86	26	86						U. S. Coin
	4	Lloyd, Supplee & Walton	27	21	25	83	1	38	5 11			Amal, Gir & Jos, Gen.
25th	5	G. C. Thompson	13	17	8	83	4	34	33 38			Button, Base
	6	Do	10	81	10	52		29	2 64			Button, Wtch Case & Pieces.
	7	Drexel & Co.	6	62	6	17		45	6 43			Amal, Wyoming
	8	Jas. Arnold	2	98	2	98						Button
	9	J. C. White	13	05	12	64		41	3 15			D.P.
	80	Hastings & Co.	8	91	8	90		01	11			Ring
	1	A. Loudon Snowden, Supt.	154	71	154	70		01	007			Bars, U. S. A. O. N. C.
	2	Do	1	50	1	48		02	2 00			Bar, U. S. A. O. N. C.
	3	Thos. Kitchen, Cashr.	14	19	14	19						Bar, Canada
26th	4	J. T. Cake, President	3	35	2	99		36	12 00			Amal & Crushed Quartz N. C.
	5	G. C. Thompson	11	49	10	87		62	5 63			Wtch Cases & Jewelry
	6	Jos. P. Mumford, Cashr.	14	97	13	16	1	81	12 07			Amal, Geo.
	7	Johnson & Lund	9	04	8	91		13	1 44			D.P. & Fillings
	8	J. H. Lyon	16	55	16	53		02	12			For. & U.S. Coin, Jewelry &c.
27th	9	G. C. Thompson	31	99	29	43	2	56	8 00			Jewelry
	90	Do	21	15	17	95	3	20	1 55			Jewelry, Bar & Wtch cases.
	1	Do	6	18	6	16		02	33			Button, Gen.
	2	Do	8	25	7	18	1	07	13 37			Button, Base
	3	Thos. R. Lee	136	73	136	65		08	06			Bar
	4	J. E. Raymond	5	96	5	77		19	3 00			Jewelry Silver
	5	H. Cowperthwait	9	12	3	43	5	69	63 22			Leaf with rags
28th	6	G. C. Thompson	11	20	6	44	4	76	43 27			Button, Base
	7	Simons, Bro. & Co.	81	30	81	12		18	22			Bars
	8	H. Muhr's Sons	17	42	17	42						Bars
	9	G. C. Thompson	36	45	34	90	1	55	4 37			Wtch Cases & Jewelry
	400	Clark & Haas	5	79	5	78		01	17			Bar
	1	Johnson & Lund	7	00	6	91		09	1 28			D.P. & Fillings
			941	22	896	51	44	71	.5 06			

Notes of Melter & Refiner. 5/3/80

The deposits are from the following sources:

N. Carolina	(2)	3
Georgia	(1)	3
Wyoming		1
Canada	(1)	1
Finer bullion	(4)	10
Jewelry & Cases		10
Very base		5
Dental Plate		3
Coin		2
Total		38

The loss on the N. Carolina mixt metal 12% is very full, but may be ascribed in great measure to the $3\frac{1}{3}$ oz. melted; — that on the Georgia mixt metal, 5.11%, is fair; — that on the Georgia amalgam, 12.07%, is quite full; — on the Wyoming amalg. 6.43%, is below the general average.

The loss on the finer bullion, 0.3%, is very small; — on Jewelry & cases, 8.76%, is moderate; — on very base 40.47%, is very high largely due to the small deposit of leaf & rags, which lost $\frac{2}{3}$ of its weight, in dirt &c.

The loss on coin, .06%, is not excessive; — on dental plate, 1.96%, about the general average

Jas C Booth
M & R

For week ending February 28th 1880

Approximate value, $ 13,895.90

To the Director of the Mint.

J. Robley Dunglison Register.

RG104 E-1 Box 120

Report of Gold Deposits
melted for week ending
February 28th 1888

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits melted for week ending: -

February 28, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]